

DuPont™ Sontara®

Fabric Technical Data - Style 9949

Property		Value	Unit	Test method
Composition	Polyester	48	%	WSP 130.1
	Woodpulp	52	%	
Basis weight		69	g/m ²	
Thickness		0.39	mm	
Absorbency		490	%	WSP 10.1
Extrinsic absorption capacity		337	ml/m ²	WSP 10.2
Grab tensile breaking strength (dry)	MD	167	N	ASTM D5034
	XD	75	N	
Strip tensile breaking strength (dry)	MD	191	N	WSP 110.4
	XD	50	N	

MD- LENGTHWISE, XD- CROSSWISE